




กระดาษอาร์ตสองหน้า ทีที



Substance (g/m ²)	190	210	260	300	350	± 4%
Thickness (µm)	157	189	240	284	331	± 10
Opacity (%)	96.0	97.0	98.0	98.0	99.0	± 1.5
Printing side						
Whiteness (%)	115	115	115	115	115	± 3
ISO Brightness (%)	88.0	88.0	88.0	88.0	88.0	± 3.0
Gloss 75° (%)	74	72	72	72	70	± 5
Surface pH	-	-	-	-	-	-
Surface roughness (µm)	≤1.5	≤ 2.0	≤ 2.0	≤ 2.0	≤ 2.0	≤ 2.0
Reverse Side						
Whiteness (%)	-	-	-	-	-	-
ISO Brightness (%)	88.0	88.0	88.0	88.0	88.0	± 3.0
Surface roughness (µm)	≤1.5	≤ 2.0	≤ 2.0	≤ 2.0	≤ 2.0	≤ 2.0
UPDATED: DECEMBER 2017						