



Substance (g/m <sup>2</sup> )	190	210	230	260	300	± 4%
Thickness (µm)	165	183	202	235	275	± 10
Opacity (%)	98.5	98.5	98.5	98.5	98.5	± 1.5
<b>Printing side</b>						
Whiteness (%)	-	-	-	-	-	-
ISO Brightness (%)	88.5	88.5	88.5	88.5	88.5	± 1.5
Gloss 75° (%)	70	70	70	70	70	± 5
Surface pH	-	-	-	-	-	-
Surface roughness (µm)	1.4	1.4	1.4	1.4	1.4	≤ 1.4
<b>Reverse Side</b>						
Whiteness (%)	-	-	-	-	-	-
ISO Brightness (%)	88.5	88.5	88.5	88.5	88.5	± 1.5
Surface roughness (µm)	1.4	1.4	1.4	1.4	1.4	≤ 1.4
UPDATED: JANUARY 2016						