




กระดาษอาร์ตมัน/ด้านสองหน้า เคจีเอ็กซ์ และ เคเอ็มเอ็กซ์



KGX Specifications - กระดาษอาร์ตมันสองหน้า

Substance (g/m ²)	80	89	95	104	113	118	128	157	± 4%
Thickness (µm)	63	70	76	83	91	96	106	132	± 4%
Opacity (%)	90.7	92.3	93.6	94.5	95.0	95.8	96.4	97.6	-
F side									
Whiteness (%)	-	-	-	-	-	-	-	-	-
ISO Brightness (%)	89.3	89.5	90.0	90.0	90.4	89.6	90.0	91.3	-
Gloss 75° (%)	70.4	72.9	72.2	70.0	68.5	73.0	71.5	67.6	± 4
Surface smoothness (sec)	4,250	5,350	4,731	4,020	3,610	4,978	3,860	2,860	-
W Side									
Whiteness (%)	-	-	-	-	-	-	-	-	-
ISO Brightness (%)	-	-	-	-	-	-	-	-	-
Gloss 75° (%)	71.6	68.7	67.9	70.4	66.6	70.6	69.6	67.2	-
Surface smoothness (sec)	4,740	4,660	4,449	4,130	3,180	4,503	3,430	2,910	-
UPDATED: JULY 2014									

KMX Specifications - กระดาษอาร์ตด้านสองหน้า

Substance (g/m ²)	80	89	95	104	113	118	128	157	± 4%
Thickness (µm)	73	82	87	99	105	114	128	159	± 4%
Opacity (%)	88.8	91.7	92.2	93.5	94.4	95.1	96.7	98.0	-
F side									
Whiteness (%)	-	-	-	-	-	-	-	-	-
ISO Brightness (%)	92.3	93.3	92.5	92.1	92.8	93.0	91.6	91.2	-
Gloss 75° (%)	-	-	-	-	-	-	-	-	-
Surface smoothness (sec)	701	650	527	516	644	447	538	309	-
W Side									
Whiteness (%)	-	-	-	-	-	-	-	-	-
ISO Brightness (%)	-	-	-	-	-	-	-	-	-
Gloss 75° (%)	-	-	-	-	-	-	-	-	-
Surface smoothness (sec)	684	684	596	518	664	562	531	401	-
UPDATED: JULY 2014									

